

Typ materiálu	Remanence Br		Koercivita Hcb		Vnitřní koercivita Hci		Hustota energie (BH) max	
	KG	T	KOe	KA/m	KOe	KA/m	MGOe	KJ/m <sup>3</sup>
N35	11.4-11.8	1.18-1.28	≥ 10.8	≥ 836	≥ 12	≥ 955	33-36	263-287
N38	11.8-12.3	1.18-1.28	≥ 10.8	≥ 860	≥ 12	≥ 955	36-39	287-310
N40	12.7-12.9	1.27-1.29	≥ 11.0	≥ 876	≥ 12	≥ 955	38-41	303-326
N42	12.9-13.3	1.29-1.33	≥ 10.5	≥ 836	≥ 12	≥ 955	40-43	318-342
N45	13.3-13.8	1.33-1.38	≥ 9.5	≥ 756	≥ 12	≥ 955	43-46	342-366
N48	13.8-14.2	1.38-1.42	≥ 10.5	≥ 835	≥ 12	≥ 955	46-49	366-390
N50	13.8-14.5	1.38-1.45	≥ 10.5	≥ 835	≥ 11	≥ 955	47-51	374-406
N52	14.3-14.8	1.43-1.48	≥ 10.8	≥ 860	≥ 11	≥ 876	50-53	398-422
33M	11.4-11.8	1.14-1.18	≥ 10.3	≥ 820	≥ 14	≥ 1114	31-33	247-263
35M	11.8-12.3	1.18-1.23	≥ 10.8	≥ 860	≥ 14	≥ 1114	33-36	263-287
38M	12.3-12.7	1.23-1.27	≥ 11.0	≥ 876	≥ 14	≥ 1114	38-41	303-326
40M	12.7-12.9	1.27-1.29	≥ 11.4	≥ 907	≥ 14	≥ 1114	38-41	303-326
42M	12.8-13.2	1.28-1.32	≥ 11.6	≥ 923	≥ 14	≥ 1114	40-43	318-342
45M	13.2-13.8	1.32-1.38	≥ 11.8	≥ 939	≥ 14	≥ 1114	43-46	342-366
48M	13.6-14.0	1.36-1.40	≥ 11.8	≥ 939	≥ 14	≥ 1114	46-49	366-390
50M	14.0-14.5	1.40-1.45	≥ 13.0	≥ 1033	≥ 14	≥ 1114	48-51	382-406
30H	10.8-11.4	1.08-1.14	≥ 10.2	≥ 812	≥ 17	≥ 1353	28-31	223-247
33H	11.4-11.8	1.14-1.18	≥ 10.6	≥ 844	≥ 17	≥ 1353	31-33	247-263
35H	11.8-12.3	1.18-1.28	≥ 11.0	≥ 876	≥ 17	≥ 1353	33-36	263-287
38H	12.3-12.7	1.23-1.27	≥ 11.2	≥ 890	≥ 17	≥ 1353	36-39	287-310
40H	12.7-12.9	1.27-1.29	≥ 11.5	≥ 915	≥ 17	≥ 1353	38-41	303-326
42H	12.8-13.2	1.28-1.32	≥ 12.0	≥ 955	≥ 17	≥ 1353	40-43	318-342
45H	13.2-13.5	1.32-1.38	≥ 12.0	≥ 955	≥ 17	≥ 1353	42-46	335-366
46H	13.3-13.8	1.33-1.38	≥ 12.2	≥ 972	≥ 16	≥ 1274	44-47	350-374
48H	13.6-14.3	1.36-1.43	≥ 12.5	≥ 995	≥ 16	≥ 1274	46-49	366-390
30SH	10.8-11.4	1.08-1.14	≥ 10.0	≥ 796	≥ 20	≥ 1672	28-31	223-247
33SH	11.4-11.8	1.14-1.18	≥ 10.5	≥ 836	≥ 20	≥ 1672	31-34	247-276
35SH	11.8-12.3	1.18-1.23	≥ 11.0	≥ 876	≥ 20	≥ 1672	33-36	263-287
38SH	12.3-12.7	1.23-1.27	≥ 11.4	≥ 907	≥ 20	≥ 1972	36-39	287-310
40SH	12.5-12.8	1.25-1.28	≥ 11.8	≥ 939	≥ 20	≥ 1972	38-41	302-326
42SH	12.8-13.2	1.28-1.32	≥ 11.8	≥ 939	≥ 20	≥ 1672	40-43	320-343
45SH	13.2-13.8	1.32-1.38	≥ 12.6	≥ 1003	≥ 20	≥ 1592	43-46	342-366
30UH	10.8-11.4	1.08-1.14	≥ 10.2	≥ 812	≥ 25	≥ 1990	28-31	223-247
33UH	11.3-11.7	1.13-1.17	≥ 10.7	≥ 852	≥ 25	≥ 1990	31-33	247-263
35UH	11.7-12.1	1.17-1.21	≥ 10.7	≥ 852	≥ 25	≥ 1990	33-36	263-287
38UH	12.1-12.5	1.21-1.25	≥ 11.4	≥ 907	≥ 25	≥ 1990	36-39	287-310
40UH	12.5-12.8	1.25-1.28	≥ 11.4	≥ 907	≥ 25	≥ 1990	38-41	302-326
28EH	10.5-10.8	1.05-1.08	≥ 9.5	≥ 756	≥ 30	≥ 2388	26-29	207-231
30EH	10.8-11.4	1.08-1.14	≥ 9.5	≥ 756	≥ 30	≥ 2388	28-31	223-241
33EH	11.3-11.7	1.13-1.17	≥ 10.2	≥ 812	≥ 30	≥ 2388	31-33	247-263
35EH	11.7-12.1	1.17-1.21	≥ 10.2	≥ 812	≥ 30	≥ 2388	33-36	263-287
38EH	12.1-12.5	1.21-1.25	≥ 11.4	≥ 907	≥ 30	≥ 2388	36-39	287-310
30AH	10.8-11.3	1.08-1.13	≥ 10.2	≥ 812	≥ 35	≥ 2785	28-32	223-255
33AH	11.2-11.7	1.12-1.17	≥ 10.2	≥ 812	≥ 35	≥ 2785	31-34	247-271